



CHI HWA
ADVERTISING

奇華廣告事業有限公司

規格厚薄公差範圍

| 壓克力板材厚度 | 國際標準 D 4802-10 厚薄公差 (約 ± 10%) | 場內厚薄公差 (約 ± 6%) |
|---------|-------------------------------------|--------------------|
| 2 mm | ± 0.2 mm | ± 0.16 mm (± 8%) |
| 3 mm | ± 0.3 mm | ± 0.2 mm |
| 4 mm | ± 0.4 mm | ± 0.25 mm |
| 5 mm | ± 0.5 mm | ± 0.3 mm |
| 6 mm | ± 0.6 mm | ± 0.35 mm |
| 8 mm | ± 0.8 mm | ± 0.5 mm |
| 9 mm | ± 0.9 mm | ± 0.54 mm |
| 10 mm | ± 1.0 mm | ± 0.6 mm |
| 12 mm | ± 1.2 mm | ± 0.72 mm |
| 13 mm | ± 1.3 mm | ± 0.8 mm |
| 15 mm | ± 1.5 mm | ± 1.0 mm |
| 20 mm | ± 2.0 mm | ± 1.2 mm |
| 25 mm | ± 2.5 mm | ± 1.5 mm |
| 30 mm | ± 3.0 mm | ± 1.8 mm |
| 35 mm | ± 3.5 mm | ± 2.1 mm |
| 40 mm | ± 4.0 mm | ± 2.4 mm |
| 45 mm | ± 4.5 mm | ± 2.7 mm |
| 50 mm | ± 5.0 mm | ± 3.0 mm |
| 55 mm | ± 5.5 mm | ± 3.3 mm |
| 60 mm | ± 6.0 mm | ± 3.6 mm |
| 65 mm | ± 6.5 mm | ± 3.9 mm |
| 70 mm | ± 7.0 mm | ± 4.2 mm |
| 80 mm | ± 8.0 mm | ± 4.8 mm |
| 90 mm | ± 9.0 mm | ± 5.4 mm |
| 100 mm | ± 10.0 mm | ± 6.0 mm |

P.S 壓克力厚許可公差依國際標準為正負10%